



B-FLEX ITALIA S.r.l.

Via 1° Maggio, 44
36050 Sovizzo (VI) ITALY
Ph +39 0444.028139
info@b-flexitalia.com

www.b-flexitalia.com

follow us on



GIMME 5 EVO

**BF FIVEPRINT TOP/G
BF FIVEPRINT TOP/M**



FIVE BF PRINTTOP/G - M

PRODUCT DESCRIPTION

FIVE BFPRINTTOP/G (semi-glossy) – FIVE BFPRINTTOP/M (matte), are two thin polyurethane white films printable with solvent, eco-solvent and latex inks and are suitable for heat transfer IN ONLY 4 SECONDS on cotton fabrics, polyester, nylon LYCRA® and acrylic garments.

Very small letters and logos can be easily cut by all current cutting plotters after the printing process thanks to the self-adhesive PET film carrier; we recommend the BF MYLAR film as a transfer tape and as a protection during the heat transfer, and then remove it while hot.

APPLICATION INSTRUCTIONS

- Print FIVE BFPRINTTOP / G-M
- Wait at least 8 hours after printing, before proceeding cut.
- Cut FIVE BFPRINTTOP / G-M with a laser 45 ° blade.
- Weed the FIVE BFPRINTTOP / G-M and remove the excess materials.
- Place the BF MYLAR film on the graphic and remove the air bubbles.
- Take off the graphic from the polyester backing.
- Pre-heat your press to 140 ° C.
- Place the garment on the lower platen of your heat press.
- Place FIVE BFPRINTTOP / G-M design on the garment.
- Press at 140 ° C for 4 seconds.
- Peel the BF MYLAR.

STANDARD SIZES

- H 150 cm => available lengths:
(upon request)
- H 100 cm => available lengths:
(upon request)
- H 75 cm => available lengths:
(upon request)
- H 50 cm => available lengths:
25 mt / 12,5 mt / 5 mt / 1 mt (standard)

APPLICATION TIPS

- Recommended fibers: organic, synthetic, mixed
- Ability to cut design as small as 0.1 cm

TECHNICAL DATA

Film:	PU/ Polyurethane
Thickness:	60 μ (±5%)
Carrier:	PET film – self adhesive

APPLICATION

Temperature:	140°C - 285° F
Time:	4"
Pressure:	medium – 3,5 bar – 50 PSI

LINER REMOVAL

Hot

WASH RESISTANCE

First wash:	wait 12 hours after application
Max wash Temp.:	40° C
Dry clean:	NO
Softener:	NO
Bleach:	NO
Dryer:	NO

SAFETY NOTICE

The values reported in this document are average values as tested under normal conditions in our lab. We cannot provide a guarantee regarding the information abovementioned in this page.

Due to possible variations in the production of garments, B-FLEX recommends testing the material prior to all applications.

This spec sheet is valid for the following products:
FIVE BFPRINT TOP G/M. Rev_2019 / 09.