













## MEDIATEX® Double Face FR



	Einheit Unit	Norm Standard	Wert Value
Substrat Substrate		DIN 60001	100% Polyester 100% polyester
Bindung Weave		DIN ISO 9354	Gewebe woven fabric
Flächengewicht Weight	 g/m <sup>2</sup>	DIN EN ISO 2286-2	270 ± 25
Brandverhalten Fire retardancy		DIN 4102 B1, ÖNORM A3800	ja yes
Tintenart Type of ink		  	alle Solventtinten, UV-härt*., Latextinten all kinds of solvent, UV-curable*, latex inks
Anwendung Application			innen indoor
Breite Width	 cm inch	DIN EN ISO 2286-1	max. 310 max. 122
Druckseite Print side			beidseitig both-sided
Rollenlänge Roll length	 m		30 - 50 ± 0,5

### Anwendungen Applications



Messebau / trade show graphic  
Backdrops / backdrops  
Blockout / blockout  
Deckenabhängiger / ceiling construction

### Besonderheiten Characteristics

- höchste Druckqualität  
highest print quality
- kein Schüsseln  
no curling
- kein Weißbruch  
no white cracking / crazing
- beidseitig bedruckbar  
printable on both sides
- leichte Montage  
easy to mount
- kalt schneidbar  
trimming cold
- extrem leichtes Blockout  
extremely light blockout

\* Da UV-härtende Tinten noch nachhärten, ist mit curling zu rechnen.

Please consider the risk of curling because UV-curable inks will still be hardening after a while.

All details are nominal values and are subject to change within usual tolerances (± 5%). The information provided in this document is based on current knowledge and experience. They do not exempt a manufacturer/processor from carrying out their own tests and trials as their in-house handling and manufacturing processes can have a significant range of influences on outcomes. Application, utilisation and processing of products is taking place outside of our control and are therefore the sole responsibility of the manufacturer/processor. date: 09/2017